

Adflex Q 401 F

Advanced Polyolefin

Product Description

Adflex Q 401 F is a reactor TPO (thermoplastic polyolefin) manufactured using LyondellBasell's proprietary *Catalloy* process technology. It is suitable for air quenched blown film applications. It contains slip and anti-block additives.

For regulatory compliance information, see the Adflex Q 401 F Product Stewardship Bulletin (PSB).

Product Characteristics

Status	Commercial: Active
Test Method used	ISO
Availability	North America, Asia-Pacific, Australia/NZ, Africa-Middle East, Latin America
Features	High Heat Resistance , Good Puncture Resistance , Good Tear Strength
Typical Customer Applications	Blown Film, Film

Typical Properties	Method	Value	Unit
Physical			
Density (Method A)	ISO 1183	0.89	g/cm ³
Melt flow rate (MFR) (230 °C/ 2.16 kg)	ISO 1133	0.65	g/10 min
Mechanical			
Tensile Stress at Break (23 °C)	ISO 527-1, -2	21	MPa
Tensile Stress at Yield (23 °C)	ISO 527-1, -2	15	MPa
Tensile Strain at Break (23 °C)	ISO 527-1, -2	>800	%
Tensile Strain at Yield (23 °C)	ISO 527-1, -2	27	%
Flexural modulus (23 °C)	ISO 178	480	MPa
Impact			
Notched izod impact strength	ISO 180		
(- 40°C, Type 1, Notch A)		4	kJ/m ²
(23°C, Type 1, Notch A)		60	kJ/m ²
Hardness			
Shore hardness D	ISO 868/ASTM D 2240	49	
<i>Note: 15 seconds</i>			
Thermal			
Heat deflection temperature B (0.45 MPa) Unannealed	ISO 75B-1, -2	57	°C
Melting temperature	DSC	164	°C
Vicat softening temperature A/50	ISO 306	108	°C

Additional Properties

Heat Resistance, Internal Test Method: 152°C (305°F)
 Tensile Stress @ Break, MD/TD, ASTM D 882: 68/48 MPa
 Tensile Strain @ Break, MD/TD, ASTM D 882: 670/870 %
 Tensile Stress @ Yield, MD/TD, ASTM D 882: 18/15 MPa
 Secant Modulus, MD/TD, ASTM D 882: 330/300 MPa
 Dart Drop Impact, ISO 7765-1: 550 g
 Elmendorf Tear Strength, MD/TD, ISO 6383-2: 440/920 g

Film property values shown were determined on 50 µm (2.0 mil) thickness blown film extruded at 238°C (460°F), 2.5:1 BUR, with a 2 mm (80 mil) die gap.

Notes

Typical properties; not to be construed as specifications.

© LyondellBasell Industries Holdings, B.V. 2014

LyondellBasell markets this product through the following entities:

- Equistar Chemicals, LP
- Basell Sales & Marketing Company B.V.
- Basell Asia Pacific Limited
- Basell International Trading FZE
- LyondellBasell Australia Pty Ltd

For the contact details of the LyondellBasell company selling this product in your country, please visit <http://www.lyb.com/>.

Before using a product sold by a company of the LyondellBasell family of companies, users should make their own independent determination that the product is suitable for the intended use and can be used safely and legally.

SELLER MAKES NO WARRANTY; EXPRESS OR IMPLIED (INCLUDING ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE OR ANY WARRANTY) OTHER THAN AS SEPARATELY AGREED TO BY THE PARTIES IN A CONTRACT.

This product(s) may not be used in:

(i) any U.S. FDA Class I, Health Canada Class I, and/or European Union Class I Medical Devices, without prior notification to Seller for each specific product and application; or

(ii) the manufacture of any of the following, without prior written approval by Seller for each specific product and application: (1) U.S. FDA Class II, Health Canada Class II or Class III, and/or European Union Class II Medical Devices; (2) film, overwrap and/or product packaging that is considered a part or component of one of the aforementioned Medical Devices; (3) packaging in direct contact with a pharmaceutical active ingredient and/or dosage form that is intended for inhalation, injection, intravenous, nasal, ophthalmic (eye), digestive, or topical (skin) administration; (4) tobacco related products and applications; (5) electronic cigarettes and similar devices; and (6) pressure pipe or fittings that are considered a part or component of a nuclear reactor.

(iii) Additionally, the product(s) may not be used in: (1) U.S. FDA Class III, Health Canada Class IV, and/or European Class III Medical Devices; (2) applications involving permanent implantation into the body; (3) life-sustaining medical applications; and (4) lead, asbestos or MTBE related applications.

All references to U.S. FDA, Health Canada, and European Union regulations include another country's equivalent regulatory classification.

Users should review the applicable Material Safety Data Sheet before handling the product.

Addhere, Adflex, Adstif, Adsyl, Akoafloor, Akoalit, Alastian, Alathon, Alkylate, Amazing Chemistry, Aquamarine, Aquathene, Arctic Plus, Arctic Shield, Avant, Catalloy, Clyrell, CRP, Crystex, Dexflex, Duopac, Duoprime, Explore & Experiment, Filmex, Flexathene, Fueling the power to win, Get in touch with, Glacido, Hifax, Histif, Hostacom, Hostalen PP, Hostalen ACP, Ideal, Indure, Integrate, Koattro, LIPP, Lucalen, Lufflexen, Lupolen, Lupolex, Luposim, Lupostress, Lupotech, Metocene, Microthene, Moplen, MPDIOL, Nerolex, Nexprene, Petrothene, Plexar, Polymeg, Pristene, Prodflex, Pro-fax, Punctilious, Purell, Refax, SAA100, SAA101, Sequel, Softell, Spherilene, Spheripol, Spherizone, Starflex, Stretchene, Superflex, TBAC, Tebol, T-Hydro, Topyl, Trans4m, Tufflo, Ultrathene, Vacido and Valtec, are trademarks owned and/or used by the LyondellBasell family of companies.

Adsyl, Akoafloor, Akoalit, Alastian, Alathon, Aquamarine, Arctic Plus, Arctic Shield, Avant, CRP, Crystex, Dexflex, Duopac, Duoprime, Explore & Experiment, Filmex, Flexathene, Hifax, Hostacom, Hostalen, Ideal, Integrate, Koattro, Lucalen, Lupolen, Metocene, Microthene, Moplen, MPDIOL, Nexprene, Petrothene, Plexar, Polymeg, Pristene, Pro-fax, Punctilious, Purell, Sequel, Softell, Spheripol, Spherizone, Starflex, Tebol, T-Hydro, Topyl, Tufflo, Ultrathene are registered in the U.S. Patent and Trademark Office.

Release Date: 24 May 2013