

Adsy/ 5 Q 39 F

Advanced Polyolefin

Product Description

Adsy/ 5 Q 39 F is an advanced polyolefin, specially designed for use as a sealing layer in co-extruded film applications.

This grade features a very low seal initiation temperature and a low flow. It contains anti-block additives.

For regulatory information please refer to Adsy/ 5 Q 39 F Product Stewardship Bulletin (PSB).

Product Characteristics

Status	Commercial: Active
Test Method used	ISO
Availability	Europe, North America, Asia-Pacific, Australia/NZ, Africa-Middle East, Latin America
Processing Methods	Blown Film, Double Bubble
Features	Low Flow , High Heat Resistance , High Shrinkage, Good Stiffness
Typical Customer Applications	Bags & Pouches, Heavy Duty Packaging, Hygiene Film, Lamination Film, Peelable Film, Shrink Film

Typical Properties	Method	Value	Unit
Physical			
Density (Method A)	ISO 1183	0.90	g/cm ³
Melt flow rate (MFR) (230 °C/ 2.16 kg)	ISO 1133	0.9	g/10 min
Mechanical			
Flexural modulus	ISO 178	480	MPa
Thermal			
Melting temperature		132	°C
<i>Note: ISO 11357-3</i>			
Heat deflection temperature B (0.45 MPa) Unannealed	ISO 75B-1, -2	52	°C
Vicat softening temperature A/50	ISO 306	107	°C
Optical			
Haze (50 µm)	ASTM D 1003	19	%
Gloss (45°, 50 µm)	ASTM D 2457	38	
Film			
Seal initiation temperature		105	°C
<i>Note: Internal test method</i>			

Additional Properties

Film properties obtained on blown film produced with laboratory line under internal standard conditions.

Tensile Young modulus, MD/TD, ISO 527-3, 25 mm/min, 50 µm: 470/480 MPa
 Stress at Yield, MD/TD, ISO 527-3, 500 mm/min, 50 µm: 22/21 MPa
 Elongation at Yield, MD/TD, ISO 527-3, 500 mm/min, 50 µm: 16/15 %
 Stress at Break, MD/TD, ISO 527-3, 500 mm/min, 50 µm: 42/31 MPa
 Elongation at Break, MDT, ISO 527-3, 500 mm/min, 50 µm: 800/830 %

Notes

Typical properties; not to be construed as specifications.

© LyondellBasell Industries Holdings, B.V. 2014

LyondellBasell markets this product through the following entities:

- Equistar Chemicals, LP
- Basell Sales & Marketing Company B.V.
- Basell Asia Pacific Limited
- Basell International Trading FZE
- LyondellBasell Australia Pty Ltd

For the contact details of the LyondellBasell company selling this product in your country, please visit <http://www.lyb.com/>.

Before using a product sold by a company of the LyondellBasell family of companies, users should make their own independent determination that the product is suitable for the intended use and can be

used safely and legally.

SELLER MAKES NO WARRANTY; EXPRESS OR IMPLIED (INCLUDING ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE OR ANY WARRANTY) OTHER THAN AS SEPARATELY AGREED TO BY THE PARTIES IN A CONTRACT.

This product(s) may not be used in:

(i) any U.S. FDA Class I, Health Canada Class I, and/or European Union Class I Medical Devices, without prior notification to Seller for each specific product and application; or

(ii) the manufacture of any of the following, without prior written approval by Seller for each specific product and application: (1) U.S. FDA Class II, Health Canada Class II or Class III, and/or European Union Class II Medical Devices; (2) film, overwrap and/or product packaging that is considered a part or component of one of the aforementioned Medical Devices; (3) packaging in direct contact with a pharmaceutical active ingredient and/or dosage form that is intended for inhalation, injection, intravenous, nasal, ophthalmic (eye), digestive, or topical (skin) administration; (4) tobacco related products and applications; (5) electronic cigarettes and similar devices; and (6) pressure pipe or fittings that are considered a part or component of a nuclear reactor.

(iii) Additionally, the product(s) may not be used in: (1) U.S. FDA Class III, Health Canada Class IV, and/or European Class III Medical Devices; (2) applications involving permanent implantation into the body; (3) life-sustaining medical applications; and (4) lead, asbestos or MTBE related applications.

All references to U.S. FDA, Health Canada, and European Union regulations include another country's equivalent regulatory classification.

Users should review the applicable Material Safety Data Sheet before handling the product.

Addhere, Adflex, Adstif, Adsyl, Akoafloor, Akoalit, Alastian, Alathon, Alkylate, Amazing Chemistry, Aquamarine, Aquathene, Arctic Plus, Arctic Shield, Avant, Catalloy, Clyrell, CRP, Crystex, Dexflex, Duopac, Duoprime, Explore & Experiment, Filmex, Flexathene, Fueling the power to win, Get in touch with, Glacido, Hifax, Histif, Hostacom, Hostalen PP, Hostalen ACP, Ideal, Indure, Integrate, Koattro, LIPP, Lucalen, Luflexen, Lupolen, Lupolex, Luposim, Lupostress, Lupotech, Metocene, Microthene, Moplen, MPDIOL, Nerolex, Nexprene, Petrothene, Plexar, Polymeg, Pristene, Prodflex, Pro-fax, Punctilious, Purell, Refax, SAA100, SAA101, Sequel, Softell, Spherilene, Spheripol, Spherizone, Starflex, Stretchene, Superflex, TBAC, Tebol, T-Hydro, Topyl, Trans4m, Tufflo, Ultrathene, Vacido and Valtec, are trademarks owned and/or used by the LyondellBasell family of companies.

Adsyl, Akoafloor, Akoalit, Alastian, Alathon, Aquamarine, Arctic Plus, Arctic Shield, Avant, CRP, Crystex, Dexflex, Duopac, Duoprime, Explore & Experiment, Filmex, Flexathene, Hifax, Hostacom, Hostalen, Ideal, Integrate, Koattro, Lucalen, Lupolen, Metocene, Microthene, Moplen, MPDIOL, Nexprene, Petrothene, Plexar, Polymeg, Pristene, Pro-fax, Punctilious, Purell, Sequel, Softell, Spheripol, Spherizone, Starflex, Tebol, T-Hydro, Topyl, Tufflo, Ultrathene are registered in the U.S. Patent and Trademark Office.

Release Date: 13 May 2013