

## DOW HDPE DGDA-5004 NT 7 High Density Polyethylene Resin

### Overview

DOW DGDA-5004 NT 7 High Density Polyethylene (HDPE) resin is a multi-purpose polymer designed for sheet extrusion and thermoforming applications, including single-serve disposables and other thin walled containers.

#### Main Characteristics:

- · Maximum rigidity
- · High Impact Strength
- · Good Top Load Strength
- Optimized Shear Rheology for Good Processability
- Complies with U.S. FDA 21 CFR 177.1520 (c) 2.2
- · Consult the regulations for complete details.

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density	0.961 g/cm³	0.961 g/cm <sup>3</sup>	ASTM D792
Melt Index			ASTM D1238
190°C/21.6 kg	57 g/10 min	57 g/10 min	
190°C/2.16 kg	0.80 g/10 min	0.80 g/10 min	
Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Strength			ASTM D638
Yield	4600 psi	31.7 MPa	
Break	3500 psi	24.1 MPa	
Tensile Elongation			ASTM D638
Yield	7.0 %	7.0 %	
Break	1000 %	1000 %	
Flexural Modulus - 2% Secant	188000 psi	1300 MPa	ASTM D790B
Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Impact Strength	40.0 ft·lb/in²	84.1 kJ/m²	ASTM D1822 1
Hardness	Nominal Value (English)	Nominal Value (SI)	Test Method
Durometer Hardness (Shore D)	66	66	ASTM D2240
Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
Deflection Temperature Under Load			ASTM D648
66 psi (0.45 MPa), Unannealed	169 °F	76.1 °C	
Brittleness Temperature	< -105 °F	< -76.1 °C	ASTM D746
Vicat Softening Temperature	268 °F	131 °C	ASTM D1525
Melting Temperature (DSC)	271 °F	133 °C	Dow Method
Peak Crystallization Temperature (DSC)	248 °F	120 °C	Dow Method

Plaque molded and tested in accordance with ASTM D4976.

### Notes

These are typical properties only and are not to be construed as specifications. Users should confirm results by their own tests.

Form No. 400-00070291en Rev: 2009-03-02

<sup>&</sup>lt;sup>1</sup> Type S

## Product Stewardship

The Dow Chemical Company and its subsidiaries ("Dow") has a fundamental concern for all who make, distribute, and use its products, and for the environment in which we live. This concern is the basis for our Product Stewardship philosophy by which we assess the safety, health, and environmental information on our products and then take appropriate steps to protect employee and public health and our environment. The success of our Product Stewardship program rests with each and every individual involved with Dow products — from the initial concept and research, to manufacture, use, sale, disposal, and recycle of each product.

## Customer Notice

Dow strongly encourages its customers to review both their manufacturing processes and their applications of Dow products from the standpoint of human health and environmental quality to ensure that Dow products are not used in ways for which they are not intended or tested. Dow personnel are available to answer your questions and to provide reasonable technical support. Dow product literature, including safety data sheets, should be consulted prior to use of Dow products. Current safety data sheets are available from Dow.

## Medical Applications Policy

NOTICE REGARDING MEDICAL APPLICATION RESTRICTIONS: Dow will not knowingly sell or sample any product or service ("Product") into any commercial or developmental application that is intended for:

- a. long-term or permanent contact with internal bodily fluids or tissues. "Long-term" is contact which
  exceeds 72 continuous hours;
- use in cardiac prosthetic devices regardless of the length of time involved ("cardiac prosthetic devices" include, but are not limited to, pacemaker leads and devices, artificial hearts, heart valves, intra-aortic balloons and control systems, and ventricular bypass-assisted devices);
- c. use as a critical component in medical devices that support or sustain human life; or
- d. use specifically by pregnant women or in applications designed specifically to promote or interfere with human reproduction.

Dow requests that customers considering use of Dow products in medical applications notify Dow so that appropriate assessments may be conducted. Dow does not endorse or claim suitability of its products for specific medical applications. It is the responsibility of the medical device or pharmaceutical manufacturer to determine that the Dow product is safe, lawful, and technically suitable for the intended use. **DOW MAKES NO WARRANTIES, EXPRESS OR IMPLIED, CONCERNING THE SUITABILITY OF ANY DOW PRODUCT FOR USE IN MEDICAL APPLICATIONS.** 

#### **Disclaimer**

NOTICE: No freedom from infringement of any patent owned by Dow or others is to be inferred. Because use conditions and applicable laws may differ from one location to another and may change with time, the Customer is responsible for determining whether products and the information in this document are appropriate for the Customer's use and for ensuring that the Customer's workplace and disposal practices are in compliance with applicable laws and other governmental enactments. Dow assumes no obligation or liability for the information in this document. NO WARRANTIES ARE GIVEN; ALL IMPLIED WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE ARE EXPRESSLY EXCLUDED.

NOTICE: If products are described as "experimental" or "developmental": (1) product specifications may not be fully determined; (2) analysis of hazards and caution in handling and use are required; (3) there is greater potential for Dow to change specifications and/or discontinue production; and (4) although Dow may from time to time provide samples of such products, Dow is not obligated to supply or otherwise commercialize such products for any use or application whatsoever.

Europe/Middle East

# Additional Information

U.S. & Canada:	1-800-441-4369	Europe/initiale East	+32-3-450-2240
0.0.0.0.00	1-989-832-1426	Italy:	+800-783-825
Mexico:	+1-800-441-4369	•	
Latin America		South Africa	+800-99-5078
Argentina:	+54-11-4319-0100		
Brazil:	+55-11-5188-9000		
Colombia:	+57-1-219-6000	Asia Pacific	+800-7776-7776
Mexico:	+52-55-5201-4700		+603-7965-5392

www.dowplastics.com

This document is intended for use within Asia Pacific, North America

Published: 2003-10-30

North America

© 2009 The Dow Chemical Company



1900 2604 6267